



NANOTRANSPORT Project



Behaviour of aerosols released to ambient air from nanoparticle manufacturing

-A Pre-normative Study (NMP4-CT-2006-033371)

Qinglan Wu (qinglan.wu@dnv.com)

<16 April 2008>

Project participants

Det Norske Veritas

Dr. Qinglan Wu

Dr. Jan Weitzenböck

Knowledge gap identification

Project management

University of Karlsruhe

Prof. Gerhard Kasper

Dr. Martin Seipenbusch

Dipl.-Ing. Axel Binder

Experimental work and results analysis

Recommendations

Grimm Aerosol Technik GmbH & Co. KG

Dr. Hans Grimm

Dr. Jürgen Spielvogel


Monitoring equipment and measurement
techniques



Occupational health risks of nanoparticle exposure through inhalation

- **Study agglomeration dynamic** of nanoparticle aerosols after release into simulate workplace environment for specific exposure scenarios
- **Develop recommendations for EC** regarding
 - Test aerosols for nanotoxicology studies
 - Testing of filters and protective equipment in the workplace
 - Research priorities

Experimental program




Agglomeration

Continuous release

Discontinuous release

Release of primary nanoparticles (NP)






Interactions with background aerosol (BA)

$$C_{NP} \gg C_{BA}$$

$$C_{NP} \approx C_{BA}$$

$$C_{NP} \ll C_{BA}$$

Experimental Set-up





Vent: $2900 \text{ min}^{-1} = 170 \text{ m}^3/\text{h}$

HWG = Hot Wire
Generator, 5 lpm Air
 $I=4 \text{ A}$, $U=4.5 \text{ V}$

By Martin Seipenbusch, University of Karlsruhe

Continuous release of NP aerosol into a clean room: homogeneous coagulation

By M. Seipenbusch et al., University of Karlsruhe





- Nanoaerosols evolve considerably with time:
their average size increases while concentration decreases
- A relative stable particle size distribution with two characteristic peaks in the range of 20 -100 nm appear after certain initial time

Continuous NP aerosol source in a simulated ambient background: scavenging/ heterogeneous coagulation



MANAGING RISK


By M. Seipenbusch et al., University of Karlsruhe



- Natural background aerosols are scavengers for NP
- The agglomeration kinetic can be well described by using a aerosol dynamic model developed

Prediction of Pt NP number concentrations in present of background aerosols

By M. Seipenbusch et al., University of Karlsruhe



- Good correlation between equilibrium concentrations calculated and experimental values
- Key parameters controlling the NP concentration with time are: the NP source rate and primary size, air flow velocity, concentration and size of background particles

Key conclusions from the study

- Nanoaerosols evolve considerably with time
- Natural background aerosols are scavengers for NP
- The time scale for size evolution depends on concentration of NP and that of background aerosol- on the order of a few minutes to 30 min.
- NP will be present in size classes other than the one in which they were originally emitted.
- Filtration efficiency for primary NP not an issue, but agglomerates may be in the Most Penetrating Particle Size range between 100-300 nm (MPPS).

- **Test aerosols** for nanotoxicology studies
 - Aged NP aerosols (including agglomerates) and primary NP equally relevant for risk assessment in workplace environment
 - Generate test NP via aerosol phase (including aging and scavenging) to simulate the scenario of primary NP release in workplace air
- **Testing of filters** and protective equipment in the workplace
 - Consider the filter efficiency for the size range of agglomerates in addition to primary NP, with the focus on MPPS
- **Research priorities**
 - Validate and refine (existing) aerosol dynamic models for predicting NP evolution in workplace for specific scenarios
 - ...

(more information can be found on NANOTRANSPORT website:-----)



www.dnv.com

Thank you!